

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 112 959 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**04.07.2001 Bulletin 2001/27**

(51) Int Cl.7: **C01B 33/26**

(21) Application number: **00420254.5**

(22) Date of filing: **08.12.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(72) Inventor: **Poncelet, Olivier Jean Christian**  
**71102 Chalon sur Saone Cedex (FR)**

(74) Representative: **Parent, Yves**  
**KODAK INDUSTRIE**  
**Département Brevets - CRT**  
**Zone Industrielle**  
**B.P. 21**  
**71102 Chalon-sur-Saône Cédex (FR)**


(30) Priority: **27.12.1999 FR 9916532**

(71) Applicant: **EASTMAN KODAK COMPANY**  
**Rochester, New York 14650 (US)**

(54) **Method to prepare an aluminosilicate polymer**

(57) The invention relates to a method to prepare an aluminosilicate polymer of the imogolite type. The method consists in treating an aluminium halide, with an alkyl orthosilicate, with an aqueous alkali in the presence of

glass or silica particles, letting the mixture ripen at ambient temperature, and then heating it at 96-98°C for long enough for the reaction to go to completion. The conditions of synthesis of the aluminosilicate polymer are thereby improved.



*FIG. 1*

**EP 1 112 959 A1**

## Description

### FIELD OF THE INVENTION

[0001] This invention concerns a method to prepare an aluminosilicate polymer, and the use of the polymer obtained by said method in the treatment of photographic processing effluents.

### BACKGROUND OF THE INVENTION

[0002] Aluminosilicate polymers are known. A filamentous tubular crystallized aluminosilicate designated imogolite occurs naturally in volcanic ash. US Patents 4 152 404 and 4 252 779 describe the synthetic preparation of substances related to imogolites. US Patent 5 888 711 describes a method to obtain directly a fibrous aluminosilicate polymer of high purity of formula  $Al_xSi_yO_z$ , where x:y is 1 to 3 and z is from 1 to 10. A variant of this method that affords a morphological variety of this aluminosilicate polymer is described in French Patent application 2 767 128.

### SUMMARY OF THE INVENTION

[0003] The object of this invention is an improvement of the synthesis of aluminosilicate polymers as described in US Patent 5 888 711 or French Patent 2 767 128, whereby these polymers are obtained faster, more simply, and at lower cost.

[0004] The method of the invention, to prepare an imogolite-type aluminosilicate polymer, comprises the following steps:

(a) A mixed aluminium-silicon alkoxide, or a precursor of a mixed aluminium-silicon compound is treated with an aqueous alkali at a pH of between 4.5 to 6.5, keeping the molar concentration of aluminium between  $5 \times 10^{-4}$  and  $10^{-2}$  M and the Al/Si molar ratio between 1 and 3.

(b) The mixture obtained in step (a) is heated at a temperature lower than 100°C for sufficient time for the reaction to go to completion.

(c) The residual ions are removed from the mixture obtained in step (b).

[0005] This method is characterized in that step (a) is carried out in the presence of silanol groups, and in that after step (a) and before step (b) a ripening step at ambient temperature is included.

### BRIEF DESCRIPTION OF THE DRAWING

[0006] Figure 1 is a schematic depiction of a device designed to perform step (a) of the method according to the invention.

## DETAILED DESCRIPTION OF THE INVENTION

[0007] According to one embodiment a mixed aluminium-silicon precursor is formed by hydrolyzing (i) an aluminium salt, an aluminium haloalkoxide, or a mixture of such compounds, and (ii) an silicium alkoxide or chloroalkoxide, in acid conditions (Ph 2-3). Preferably, an aluminium salt such as a halide (e.g., chloride or bromide), a perhalogenate, a sulfate, a nitrate, a phosphate or a carboxylate, and a silicon alkoxide that is a methoxide or an ethoxide, for example, a tetramethyl or tetraethyl orthosilicate, can be used. The hydrolysis is carried out at ordinary temperature between 15 and 35°C, preferably between 20 and 25°C, by adding the silicon alkoxide to the aluminium salt in aqueous solution, and then adding an aqueous alkali, sodium or potassium hydroxide. The precursor is thereby obtained. According to a preferred embodiment, the aluminium salt, e.g.  $AlCl_3 \cdot 6H_2O$  is added to water and allowed to stand 10:30 minutes at room temperature. The pH of the solution is about 2. Then a silicium compound e.g. a silicium alkoxide, is added to the solution. The pH of the reaction mixture is still about 2. Then, an alkali is added to obtain the precursor.

[0008] The precursor can also be formed by mixing a silicon alkoxide or chloroalkoxide with an aluminium chloralkoxide. In this procedure, as in the one above, the alkoxyl radical preferably contains from 1 to 5 atoms of carbon, such as methoxide, ethoxide, n-propoxide, or i-propoxide.

[0009] To the precursor is then added an aqueous alkali to get a pH between 4.5 and 6.0, preferably between 5.0 and 5.5, while maintaining the concentration of Al between  $5 \times 10^{-4}$  M and  $10^{-2}$  M and the Al/Si molar ratio between 1 and 3. The aluminium concentration is advantageously set between  $5 \times 10^{-3}$  and  $7 \times 10^{-3}$ . According to another embodiment, the alkali takes the form of a water-ethanol solution. An aqueous solution of sodium or potassium hydroxide with a concentration between 2 M and  $10^{-2}$  M and advantageously between 0.1 M and 1 M is preferably used. When the alkali is added, an hydrolysis takes place and the polymeric aluminosilicate precipitates as a gel. This precipitate is collected by filtration and redissolved in acid medium to yield a limpid solution with a pH between about 3.8 and 4.5. This solution is then diluted to obtain an Al + Si content of between 0.3 and 0.8 g/l. The solution is then ready for the heating step (b).

[0010] The invention comprises the feature in that step (a) of the process, i.e. the preparation and hydrolysis of the precursor, or the hydrolysis of the mixed alkoxide, is carried out in the presence of silanol groups (SiOH). These groups can in particular be provided by silica particles or beads, which possess hydroxy groups at their surface. When the volume of liquid to be treated is large it may be desirable to increase the quantity of beads. The diameter of the beads can be between 0.2 and 5 mm and preferably between 1 and 3 mm. The op-

timal diameter is selected so as to afford optimal percolation of the liquid with minimal head loss.

**[0011]** The method of the invention comprises further the feature that the hydrolysis of step (a) is followed by ripening at ordinary temperature. This ripening operation is carried out in simple containers or open tanks made of plastic or any other inert material. The ripening requires no immobilization of any reactor. The ripening time is at least 5 days. This time allows the time required for step (b) to be considerably reduced.

**[0012]** Step (b) of the method of the invention consists in heating the product of the hydrolysis and the ripening at a temperature lower than 100°C for long enough for the reaction to go to completion. Without ripening this takes several days, during which time the reactor is immobilized. With the ripening step according to the invention the time required for the heating step can be reduced to 24 hours and even to 12 hours, while retaining a high yield of Al + Si in the final product. This heating step is carried out preferably in an inert reactor, for example made of stainless steel, ceramic or an enameled material. The inside walls of the reactor must be clean and in particular free of any substances or nuclei that favor the growth of aluminium oxides.

**[0013]** According to one embodiment, the heating is performed at 96-98°C for 24 hours. The heating step can also be carried out in the presence of silanol groups in the form of glass or silica beads analogous to those of step (a). This heating is assumed to favor a condensation resulting in the formation in solution of an aluminosilicate polymer of the imogolite type. This assumption does not restrict the scope of the invention. Indications concerning this step in the process are given in US Patent 5 888 711.

**[0014]** According to one embodiment, after the heating step the solution can be concentrated by any appropriate method, for example by ultrafiltration or centrifuging, so as to obtain a solution of concentration between about 1 and 5 g/l. The solution can also be allowed to settle, and the least dense phase collected. This phase consists of a spindle-shaped variety of an aluminosilicate polymer of the imogolite type that possesses improved antistatic properties. This embodiment is described in European Patent application 895 965.

**[0015]** According to another embodiment, a stable solid gel can be obtained by addition of an alkali to the solution of the aluminosilicate polymer. For example, ammonia can be added to the solution to obtain a pH of about 8.

**[0016]** According to another embodiment the aluminosilicate polymer can be modified by grafting onto its surface functions such as SH or  $-S(CH_2)_n-S-$  where n is in the range 0 to 4. This grafting is performed by hydrolyzing an alkylalkoxysilane comprising an SH or  $-S(CH_2)_n-S-$  function in the presence of the aluminosilicate polymer.

**[0017]** The aluminosilicate polymers obtained according to the method of the invention are particularly

useful for the extraction of metal cations or organic pollutants from aqueous effluents. Such extraction is highly advantageous for the depollution of effluents from photographic processing, such as developing, bleaching or fixing baths, or washing water from such processing.

#### EXAMPLE 1

**[0018]** In a 300-liter reactor (10) made of enameled stainless steel depicted schematically in Figure 1 was placed 100 liters of osmosed water, followed by 369 g of  $AlCl_3 \cdot 6H_2O$  (1.53 mole). The solution was allowed to stand 30 minutes at room temperature then, 129 g of tetramethyl orthosilicate (1.11 mole) were added. The resulting clear solution was stirred for 30 minutes. To this reactor, as shown in Figure 1, was fitted a circuit comprising an outlet (11) connected by piping (12), and a cartridge (13) loaded with 200 g of glass beads (14) of diameter 2 mm (Prolabo). The cartridge (13) was connected by piping (16) to a pump (15) with a flow rate of 10 liters/minute that sent the liquid back to the reactor (10). To the contents of the reactor were added 3.5 liters of 1M NaOH in 1 hour 30 minutes. The reaction medium became cloudy. The mixture was stirred for 3 hours. The mixture became clear. The pump was then disconnected and 1.060 liters of 1M NaOH then added in 1 hour. A white precipitate formed, which was allowed to settle overnight. The supernatant was then decanted. The Al + Si content of the precipitate measured by inductively coupled plasma (ICP) assay was 2.5 g/l.

**[0019]** To the precipitate was added 0.6 liters of a 50:50 mixture by volume of 1M HCl and 2M  $CH_3CO_2H$ . The mixture was stirred for 6 hours. It became clear and its pH was 4.0. This mixture was then diluted with osmosed water to obtain an Al + Si content of 0.35 g/l.

**[0020]** The diluted mixture was left to stand in a container made of inert plastic material (polypropylene) for 10 days at ambient temperature (about 20°C). This step is the ripening described above.

**[0021]** The mixture was then heated at 96°C with stirring for 24 hours in a stainless steel reactor.

**[0022]** The reaction mixture was then concentrated by ultrafiltration through an Amicon 100K (polyethersulfone) membrane. The yield of imogolite, calculated in terms of Al + Si was 15 kg of 3 g/l solution (87%).

#### EXAMPLE 2

**[0023]** The procedure of Example 1 was repeated except that the ripening step was not performed. The final yield of Al + Si was less than 40%.

#### EXAMPLE 3

**[0024]** The procedure of Example 1 was repeated, except that glass beads were not used in step (a). Instead, the same amount of glass beads was placed in the reactor in which the solution was heated. A heterogeneous

ous mixture of imogolite and boehmite was obtained ( $\text{Al}_2\text{O}_3$ ).

characterized in that glass or silica beads 0.2 to 5 mm in diameter are used in step (a).

## Claims

5

1. A method to obtain an aluminosilicate polymer of the imogolite type, comprising the steps of :

(a) contacting a mixed aluminium-silicon alkoxide, or a precursor of a mixed aluminium-silicon compound with an aqueous alkali at a pH of between 4.5 and 6.5, keeping the molar concentration of aluminium between  $5 \times 10^{-4}$  and  $10^{-2}$  M, and the Al/Si molar ratio between 1 and 3. 10 15

(b) heating the mixture obtained in step (a) at a temperature below  $100^\circ\text{C}$  for a time sufficient for the reaction to go to completion.

(c) removing the residual ions from the mixture obtained in step (b), this method being characterized in that step (a) is carried out in the presence of silanol groups, and in that after step (a) and before step (b) a ripening step at room temperature is carried out. 20 25

2. A method according to Claim 1, characterized in that step (b) is also carried out in the presence of silanol groups.

3. A method according to either of Claims 1 or 2, characterized in that the silanol groups are provided in the form of silica or glass beads. 30


4. A method according to any one of Claims 1 to 3, characterized in that said precursor of a mixed aluminium-silicon compound is a product of the hydrolysis (i) of a compound selected among the class consisting of aluminium salts, and aluminium haloalkoxides, and (ii) a compound selected from the class consisting of  $\gamma$  silicon alkoxides and chloroalkoxides. 35 40

5. A method according to any one of Claims 1 to 4, characterized in that the duration of said ripening step is in the range 5 to 15 days. 45

6. A method according to any one of Claims 1 to 5, characterized in that said precursor of a mixed aluminium-silicon compound is the result of the hydrolysis of (i) an aluminium halide and (ii) a silicon alkoxide. 50

7. A method according to Claim 6, characterized in that said precursor is obtained by adding an aluminium salt to water, then adding a silicon alkoxide, and then adding an alkali. 55

8. A method according to any one of Claims 1 to 7,



*FIG. 1*



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 00 42 0254

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	WO 96 13459 A (KODAK PATHE; EASTMAN KODAK CO (US)) 9 May 1996 (1996-05-09) * the whole document *	1-8	C01B33/26
D	& US 5 888 711 A 30 March 1999 (1999-03-30) ---		
A	FR 2 740 466 A (KODAK PATHE) 30 April 1997 (1997-04-30) * page 3, line 34 - page 4, line 10 *	1,3,8	
A	EP 0 895 965 A (EASTMAN KODAK CO) 10 February 1999 (1999-02-10) * the whole document *	1,4,7	
D	& FR 2 767 128 A 12 February 1999 (1999-02-12) ---		
A	BARRETT S M ET AL: "THE SYNTHESIS AND CHARACTERIZATION OF IMOGOLITE" EUROPEAN POLYMER JOURNAL, GB, PERGAMON PRESS LTD. OXFORD, vol. 27, no. 7, 1991, pages 609-612, XP002007057 ISSN: 0014-3057 * the whole document *	1,4,7	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C01B
A	FR 2 385 646 A (NAT RES DEV) 27 October 1978 (1978-10-27) * claims 1,2 *	1	
D	& US 4 152 404 A 1 May 1979 (1979-05-01) ---		
		-/--	
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>30 March 2001</b>	Examiner <b>Rigondaud, B</b>
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 82 (F04021)



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 00 42 0254

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)
A	DATABASE CHEMABS 'Online! CHEMICAL ABSTRACTS SERVICE, COLUMBUS, OHIO, US; WADA, S. I. ET AL: "Synthetic allophane and imogolite" retrieved from STN Database accession no. 91:178284 CA XP002007058 * abstract * & J. SOIL SCI. (1979), 30(2), 347-55, 1979, -----	1	
A	GB 2 025 384 A (MACAULAY INST FOR SOIL RESEARC) 23 January 1980 (1980-01-23) * the whole document * -----	1	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.CI.7)
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>30 March 2001</b>	Examiner <b>Rigondaud, B</b>
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/92 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 42 0254

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

30-03-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9613459 A	09-05-1996	DE 69518909 D	26-10-2000
		EP 0741668 A	13-11-1996
		JP 9507826 T	12-08-1997
		US 5888711 A	30-03-1999
FR 2740466 A	30-04-1997	FR 2740465 A	30-04-1997
		US 5714309 A	03-02-1998
EP 0895965 A	10-02-1999	FR 2767128 A	12-02-1999
		JP 11130421 A	18-05-1999
FR 2385646 A	27-10-1978	GB 1574954 A	10-09-1980
		BE 865317 A	17-07-1978
		CA 1094778 A	03-02-1981
		CH 641127 A	15-02-1984
		DE 2813323 A	05-10-1978
		IT 1156181 B	28-01-1987
		JP 1441904 C	30-05-1988
		JP 53124199 A	30-10-1978
		JP 62038283 B	17-08-1987
		NL 7803281 A,B,	02-10-1978
		US 4252779 A	24-02-1981
		US 4152404 A	01-05-1979
GB 2025384 A	23-01-1980	CA 1135938 A	23-11-1982
		DE 2962999 D	22-07-1982
		EP 0007713 A	06-02-1980
		JP 55010498 A	24-01-1980
		US 4241035 A	23-12-1980

EPO FORM P-489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82